



# LUBRICANTS™

POWER TO PERFORM™

## RUSTOP 171

### PHYSICO-CHEMICAL PROPERTIES

	RUSTOP 171
Parameters	Typical Values
Appearance	Clear
KV at 40 °C, cSt	2.2
SALT SPRAY TEST ( ASTM B 117) ,HRS, PASS	40
Flash Point, °C	42
Specific Gravity at 15°C	0.8158
HUMIDITY CABINET TEST , HRS, PASS	>450

### FEATURES & BENEFITS

- Premium solvent cut- back type Rust Preventive oil forming a very thin film of 3-3.5 micron
- Passes water displacement test.
- Easy application and wide coverage
- Compatible with Lubricant
- Film forming content of 22 % approx. by wt.